

Keramull KM 250



Semi-technical roller. Suitable for low-medium loads. It is the ideal product in order to manufacture single and double-fired tiles.

Mineralogical composition

- Corundum
- Mullite
- Zirconia

Type

Semi-Technical

Al ₂ O ₃ content	77%
Bulk density	2.60 Kg/dm ³
Apparent porosity	21.0%
Absorbed water	10.0%
M.O.E. 20°C	> 85 GPa
Thermal expansion 20-400°C	4.9*10 ⁻⁶ K ⁻¹
Thermal expansion 20-1000°C	6.05*10 ⁻⁶ K ⁻¹

Typical use

- Single firing
- Double firing
- Gres

