Technical specifications

Keramull KM 250

Semi-technical roller. Suitable for low and medium loads. It is the ideal product in order to manufacture single and double-fired tiles.

Mineralogical composition

- Corundum
- Mullite
- Zirconia

Type

Semi-Technical

Al_2O_3 content	77%
Bulk density	2.60 Kg/dm^3
Apparent porosity	21.0%
Absorbed water	10.0%
M.O.E. 20°C	> 85 GPa
Thermal expansion 20-400°C	$4.9*10^{-6}K^{-1}$
Thermal expansion 20-1000°C	$6.05*10^{-6}K^{-1}$

Typical use

- Single firing
- Double firing
- Gres

