Rigato

Roller recommended for the production of very large and thin tiles. Its special geometry reduces the contact surface between the roller and the tile.

Mineralogical composition

- Corundum
- Mullite
- Zirconia

Type

Special Products

Al_2O_3 content	70%
Bulk density	2.80 Kg/dm^3
Apparent porosity	17.0%
Absorbed water	6.0%
M.O.E. 20°C	> 105 GPa
Thermal expansion 20-400°C	4.5*10^{-6}K^{-1}
Thermal expansion 20-1000°C	5.5*10^{-6}K^{-1}

Typical use

- According to customer requirements

